

DESCRIPTION

PRIMERFLEX PLUS is an elastic high performance, two-component urethane system designed for use as primer and sealer for porous substrates (concrete, mortar, wood,...) and sandblasted steel, for PUR or polyurea spray coatings. It also exhibits a low sensitivity to substrate moisture, leaving only minimal bubbling when applied to slightly damp surfaces. By its low viscosity PRIMERFLEX PLUS feature an excellent penetration to the substrate and allows to be recoated from 3h to 24h.

ANALYSIS OF THE COMPONENTS

| | Component A | Component B |
|--------------------|--------------------|--------------------|
| DESCRIPTION | Isocyanate | Polyol |
| Appearance | Liquid | Liquid |
| Colour | Dark Brown | Yellow |
| Mix ratio | 1 | 1 |
| | NCOv 24.1 | Ohv 107 mg KOH/g |
| Freezing point | Below 0°C (32°F) | N/A |
| Viscosity | 40 - 50 mPas | 800 - 100 |

PROPERTIES OF THE SYSTEM

| PROPERTIES | RESULT | TEST |
|-------------------------------|--------------------------|-------------|
| Solids | 100 % | |
| VOC | 0 % | |
| Elongation | 30 % ± 10% | ASTM D 412 |
| Tensile Strength | 15 mPa (2150 psi) | ASTM D 412 |
| Tear resistance (C type dice) | 200 pli | D53515 |
| Adherence | 3,5 MPa (>500 psi) | |
| Performance | 0,200 lit/m ² | |
| Drying time | | |
| Recoating min time | 3 h | |
| Recoating max time | 24 h | |
| 25°C 50% HR | | |
| Pot life @ 25°C 50%HR | 45-60 min | |

PERFORMANCE

According to porosity and irregularity of the substrate the yields can vary obviously. Please find indicative data that you will have to verify in each case:

Very porous substrates (mortar, cement,...) ... 2-3 m²/litre

Concrete, wood, sandblasted steel,... 4-5 m²/ litre

Ceramic ,elastomeric membrane,... 5-6 m²/ litre

In case of very porous substrates, with many cracks and hollows or superficial humidity it is recommended to apply more than one coat respecting drying time between coats until a maximum of 130 microns of total thickness. Avoid to leave zones with too much thickness (in irregularities or pools) since just the superior layer will cure and adhesion is not achieved

It is not recommended to apply the primer within early and late hours of the day since you may get some foam with dew. It is recommended to apply it so that it is exposed to the sun when it begins to cure.

When applying the primer with risk of rain please note that if the membrane contacts with water before curing bubbles or milky spots may appear . If so , you must sand the area to eliminate the product and recoat.

APPLICATION METHOD

PRIMERFLEX PLUS can be applied by roller or airless. Application by roller is recommended when the substrate have many cracks, holes or irregularities to be sealed and can be applied mixed with silica sand to be used as a mortar to filling up orifices or fissures

STORAGE AND TRANSPORTATION

Component A/ Isocyanate:

The original drums must be kept perfectly sealed in order to prevent contamination with moisture or any other materials that may have a negative impact on the processing of the product. This product reacts slowly with water creating polyureas and liberating CO₂, which may cause the sealed drums to expand and break.

It is recommended to store this product between 24 °C – 40 °C (75 °F – 104 °F) and it can be stored 12 months by keeping the product in the original containers properly sealed at 25 °C (77 °F).

Component B/ Aminic resin:

This product is hygroscopic and therefore the drums have to be sealed to prevent the absorption of moisture, which could affect its processing negatively. It is recommended to store this product between 10°C – 45 °C (50 °F – 113 °F) and it can be stored 12 months by keeping the product in its properly sealed original containers at 25 °C (77 °F).

HEALTH AND SAFETY INFORMATION

Appropriate literature has been assembled in order to provide information concerning the health and safety precautions that must be observed when handling PU-100 isocyanate and aminic components. Before working with these products, you must read and become familiar with the available information on their hazards, proper use and handling. This cannot be overemphasized. Information is available in several forms, e.g. material safety data sheet and product labels. Consult your ARTLUX EUROPA representative for further information.

IMPORTANT INFORMATION AND SAFETY PRECAUTIONS

Liquid irritate skin and eyes. Use chemical goggles, protective clothing and rubber gloves when working with chemical components. Vapor and spray mists may be harmful. Use only with exhaust ventilation and a positive pressure air supplied full-face respirator. Don not use if you have chronic breathing problems or if you have had a reaction to isocyanates.

The information and data contained herein are believed to be accurate and reliable; however, it is the user's responsibility to determine suitability of use. Since ARTLUX EUROPA cannot know all of the uses to which its products may be put or the conditions of use, it makes no warranties concerning the fitness or suitability of this products for particular use or purpose. Users should thoroughly test any proposed used of the ARTLUX EUROPA products and independently conclude satisfactory performance in the application. Likewise, if the manner in which the product is used requires governmental approval or clearance, the user must obtain approval.

ARTLUX EUROPA warrants only that products will meet specification as noted. There is no warranty of fitness for use, nor any other express or implied warranties. The user's exclusive remedy and ARTLUX EUROPA sole liability is limited to refund of the purchase price or replacement of any product shown to be otherwise than as warranted. ARTLUX EUROPA will not be held liable for incidental or consequential damages of any kind.

ARTLUX EUROPA EUROPA S.L.

C/ CAMPO SAGRADO 11 GIJON 33205 ASTURIAS, ESPAÑA

www.artluxeuropa.com info@artluxeuropa.com Tel. +34 985 32 33 28